CX3799823 | 2000110WP1250TAPE COEX

ConQuest® Empty Conduit, 2 in, SDR 11, orange, with pull tape

• *Product complies with the Build America, Buy America Act (BABAA) requirements of the Infrastructure Investment and Jobs Act of 2021 (Pub. L. 117- 58, §§ 70901-70953), or is the subject of a waiver approved by the Secretary of Commerce or designee. Compliance requirements and waiver applicability vary based on government funding program. Check the laws and regulations for your specific program.

Product Classification

Flexural Property Test Method

Regional Availability	North America
Product Type	Empty conduit
Product Brand	ConQuest®
Government Funding	Build America Buy America (BABA) compliant*
General Specifications	
Color	Orange
Conduit Type	Non-toneable
Density Test Method	ASTM D792A
Density, maximum	0.955 g/cm³ 0.035 lb/in³
Density, minimum	0.941 g/cm³ 0.034 lb/in³
Design Standard	ASTM D3350-05
Wall Type	Smooth
Dimensions	
Length	762 m 2500 ft
Inner Diameter, nominal	48.692 mm 1.917 in
Outer Diameter, nominal	60.325 mm 2.375 in
Wall Thickness Designation	SDR 11
Wall Thickness, minimum	5.486 mm 0.216 in
Nominal Size	2 in
Material Specifications	
Flexural Modulus, minimum	551.581 N/mm² 80000 psi

Page 1 of 2

©2024 CommScope, Inc. All rights reserved. CommScope and the CommScope logo are registered trademarks of CommScope and/or its affiliates in the U.S. and other countries. For additional trademark information see https://www.commscope.com/trademarks. All product names, trademarks and registered trademarks are property of their respective owners. Revised: April 11, 2024

ASTM D790



CX3799823 | 2000110WP1250TAPE COEX

Hydrostatic Design Basis	Not pressure rated
Hydrostatic Design Test Method	ASTM D2837
Material Type	High density polyethylene (HDPE) Polyester
Melt Flow Rate Test Method	ASTM D1238
Melt Flow Rate, maximum	0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported	660.4 mm 26 in
Tensile Property Test Method	ASTM D638
Tensile Strength at yield, minimum	20.684 N/mm² 3000 psi
Breaking Strength	566.99 kg 1250 lb
Pull Line Type	Таре
Pulling Tension, maximum	1,408.404 kg 3105 lb

Environmental Specifications

Environmental Stress Crack Resistance	Failure rate of 10% within 96 hours
Environmental Stress Test Method	ASTM D1693, ESCR Condition B

Packaging and Weights

Weight, net

952.425 kg/km | 640 lb/kft

Regulatory Compliance/Certifications

Agency

Classification

ISO 9001:2015

Designed, manufactured and/or distributed under this quality management system



* Footnotes

Environmental Stress Crack Resistance ESCR-Environmental Stress Crack Resistence

Page 2 of 2

